

**TECHNICALDATASHEET** 

Version: October 2012

PAGE 1

## GG 416 T 2x2 TWILL CARBON FABRIC

| CHARACTERISTICS    |                  | Nominal   | Tolerance | Normative     |  |
|--------------------|------------------|-----------|-----------|---------------|--|
| Mass per unit area | g/m <sup>2</sup> | 416       | ± 5%      | ISO 4605      |  |
| Weave              |                  | 2x2 Twill |           | ISO 2113      |  |
| Width              | mm               | 1000/1200 | ± 2,5%    | ISO 22198     |  |
| Thickness          | mm               | 0,42      | ±2,5%     | ISO 5084 (**) |  |
| Other informations |                  | Loomstate |           |               |  |

| Nominal Construction | W                    | ARP                  | WEFT                           |                        |
|----------------------|----------------------|----------------------|--------------------------------|------------------------|
| Fiber Description    |                      | bon Fiber<br>800 tex | HR Carbon Fiber<br>12K 800 tex |                        |
| Fibre Producer       | GI                   | RAFIL                | GRAFIL                         |                        |
| Thread Count         | 2,6 ends/cm          | ISO 4602             | 2,6 ends/cm                    | ISO 4602               |
| Weight Distribution  | 212 g/m <sup>2</sup> | 49%                  | 216 g/m <sup>2</sup>           | 51%                    |
|                      | 12K Carbon 208       | 8/ 50%               | 12K Carbon 208/ 50%            |                        |
| Selvedges            | Weaving style        | LENO                 | Type of Fiber                  | HM polyester<br>22 tex |

(\*\*) Theorical thickness for an epoxy laminate with 40% of reinforcement in volume.

NOTE: Technicalinformation furnished is based on laboratory findings and believed to be correct. Nowarranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.