



PYROFIL™ TR30S

Typical Properties Of PYROFIL TR30S

Tow Tensile	Strength	640 4410	ksi MPa	JISR 7601
	Modulus	34 235	msi GPa	
Typical Density		0.065 1.79	lb.in ³ g/cm ³	JISR 7601
Typical Yield	3K	2480 200	yds/lb mg/m	JISR 7601
Typical Yield	6K	1241 400	yds/lb mg/m	JISR 7601

Important: The technical information contained herein is not to be construed as warranties and no patent liability can be assumed. This information can be used for material selection purposes only.

5900 88th Street
Sacramento, CA
95828, USA
Tel: 916.386.1733
Fax: 916.383.7668
Web: www.grafil.com



ISO 9001:2000
FM 56416

02/2008