

## Technical Datasheet - MILLIFOAM® DIV80H

MILLIFOAM® DIV80H is a closed-cell, rigid polymer foam based on polyvinylchloride (PVC) chemistry. It offers excellent mechanical properties to low weight and is ideal for applications subjected to fatigue, slamming or impact loads. With its excellent mechanical properties to weight, it is the foam of choice for marine, land transportation, wind energy, civil infrastructure and general industrial markets.

Polymer	PVC	Sheet Size	2440 x 610 mm
Thickness range	0.5-5.0 mm	Supplier	Diab Group

MILLIFOAM® DIV80H is compatible with all commonly used resin and manufacturing systems with a maximum processing temperature of 90 °C. The foam has an excellent chemical resistance, low water absorption and good thermal/acoustic insulation properties including a consistent high-quality surface structure. It has a low resin uptake and is fast and easy to process and therefore an all-purpose material for the use in multiple industries.

MILLIFOAM® DIV80H Properties*	
Density	80 kg/m <sup>3</sup>
Compressive Strength	1.4 MPa
Compressive Modulus	90 MPa
Tensile Strength	2.5 MPa
Tensile Modulus	95 MPa
Shear Strength	1.15 MPa
Shear Modulus	27 MPa
Coefficient of Thermal Expansion	4.0 1/K*10E-5
Thermoforming Temperature	90-120°C (194-248°F)

\*Data refer to original vendor information

For more information please visit our homepage [www.4a-manufacturing.at](http://www.4a-manufacturing.at) or contact us directly by phone or e-mail.

#### DISCLAIMER:

MILLIFOAM® is a registered trademark of the 4a technology group and its subsidiaries. The presented data and technical advice are based on current knowledge and original vendor information which may change at any time.